

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 4, 2023

Ms. Sandy DePriest
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 53237
Invoice No. 84550

Dear Ms. DePriest:

One (1) fabric sample, identified as **ALETA IMO**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the rest; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” ***Per your request, testing was modified by using flame retardant polyurethane foam.***

The sample submitted was tested to Section 3.1 Smouldering Cigarette Test. The results are as follows:

Test Results

Smouldering Cigarette

#1
PASS

#2
PASS

(No flaming ignition or progressive smouldering ignition)

(No flaming ignition or progressive smouldering ignition)


The sample submitted **meets** minimum requirements of the above standard when tested to the smouldering cigarette ignition source.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 4, 2023

Ms. Sandy DePriest
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 53237
Invoice No. 84550

Dear Ms. DePriest:

One (1) fabric sample, identified as **ALETA IMO**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” ***Per your request, testing was modified by using flame retardant polyurethane foam.***

The sample submitted was tested to Section 3.2 Propane Flame Test. The results are as follows:

Test Results

Propane Flame

#1
PASS

#2
PASS

(No flaming ignition or progressive smouldering ignition)

(No flaming ignition or progressive smouldering ignition)


The sample submitted **meets** minimum requirements of the above standard when tested to the propane ignition source.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 14, 2022

Ms. Sandy DePriest
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 52628
Invoice No. 83961

Dear Ms. DePriest:

One (1) fabric sample, identified as **Aleta Cobblestone**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
10mm	12mm	11mm


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 14, 2022

Ms. Sandy DePriest
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 52628
Invoice No. 83961

Dear Ms. DePriest:

One (1) fabric sample, identified as **Aleta Cobblestone**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2019 Edition", (Cover Fabric Test). The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
13mm	10mm	11mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

