

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 14, 2022

Ms. Sandy DePriest
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 52628
Invoice No. 83961

Dear Ms. DePriest:

One (1) fabric sample, identified as **Ashida Dusty Rose**, was received and tested in accordance with the test procedures outlined. The results are as follows:

Test Results

<u>Test Procedures</u>	<u>Warp</u>	<u>Fill</u>
Breaking Strength (lbf) ASTM D 5034-21 (Grab)	286.2	148.8
Yarn Slippage (lbf) ASTM D 4034-19	90.4	94.9
Resistance to Pilling ASTM D 3511-16 (Brush)	5 – No Pilling	
Colorfastness to Crocking AATCC 8-2016	Dry – 5 Wet – 5	
Colorfastness to Light (40 hrs) AATCC 16.3-2020	Grade 4-5	
Surface Abrasion ASTM D 4157-13 (#10 Cotton Duck Abradant) 4lb. Tension, 3lb. Load	Passed 60,000 Cycles*	


*Testing was stopped at this point, sample had not failed

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 14, 2022

Ms. Sandy DePriest
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 52628
Invoice No. 83961

Dear Ms. DePriest:

One (1) fabric sample, identified as **Ashida Dusty Rose**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
14mm	14mm	13mm


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 14, 2022

Ms. Sandy DePriest
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 52628
Invoice No. 83961

Dear Ms. DePriest:

One (1) fabric sample, identified as **Ashida Dusty Rose**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2019 Edition", (Cover Fabric Test). The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
15mm	15mm	16mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

