

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 10, 2018

Ms. Amy Bermudez
RICHLOOM FABRICS GROUP
261 Fifth Avenue
New York, NY 10016

Reference: Laboratory Test Report
Lab Identification No. 31749
Invoice No. 62949

Dear Ms. Bermudez:

One (1) fabric sample, identified as **PATTERN: BONA 102; COLOR: BLUE; FINISH: SR/BS1**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MCS.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” **Testing was performed using a non-flame retardant polyurethane foam with a density of 22 kg/m³.**

The sample submitted was tested to Section 3.1 Smouldering Cigarette Test. The results are as follows:

Test Results

Ignition Source

Smouldering Cigarette	#1	PASS (No flaming or progressive smouldering)
	#2	PASS (No flaming or progressive smouldering)

The sample submitted **meets** minimum requirements of the above standard when tested to the smouldering cigarette ignition source.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 10, 2018

Ms. Amy Bermudez
RICHLOOM FABRICS GROUP
261 Fifth Avenue
New York, NY 10016

Reference: Laboratory Test Report
Lab Identification No. 31749
Invoice No. 62949

Dear Ms. Bermudez:

One (1) fabric sample, identified as **PATTERN: BONA 102; COLOR: BLUE; FINISH: SR/BS1**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MCS.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” **Testing was performed using a non-flame retardant polyurethane foam with a density of 22 kg/m³.**

The sample submitted was tested to Section 3.2 Propane Flame Test. The results are as follows:

Test Results

Ignition Source

Propane Flame	#1	PASS (No flaming or progressive smouldering)
	#2	PASS (No flaming or progressive smouldering)

The sample submitted **meets** minimum requirements of the above standard when tested to the propane ignition source.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 2, 2018

Ms. Amy Bermudez
RICHLOOM FABRICS GROUP
261 Fifth Avenue
New York, NY 10016

Reference: Laboratory Test Report
Lab Identification No. 31608
Invoice No. 62837

Dear Ms. Bermudez:

One (1) fabric sample, identified as **PATTERN: BONA 102; COLOR: BLUE; FINISH: SR & BK**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths

13mm

14mm

14mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 2, 2018

Ms. Amy Bermudez
RICHLOOM FABRICS GROUP
261 Fifth Avenue
New York, NY 10016

Reference: Laboratory Test Report
Lab Identification No. 31608
Invoice No. 62837

Dear Ms. Bermudez:

One (1) fabric sample, identified as **PATTERN: BONA 102; COLOR: BLUE; FINISH: SR & BK**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2013 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

10mm 13mm 12mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

