



**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

April 11, 2019

Mr. Logan Jones  
RICHLOOM FABRICS GROUP  
P.O. Box 1157  
Clinton, SC 29325

Reference: Laboratory Test Report  
Lab Identification No. 35376  
Invoice No. 66580

Dear Mr. Jones:

One (1) fabric sample, identified as **EMMERLING WHITE FOR RADISSON (NINA NICKERSON)**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

**Test Results**

Vertical Char Lengths

8mm

8mm

8mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

April 11, 2019

Mr. Logan Jones  
RICHLOOM FABRICS GROUP  
P.O. Box 1157  
Clinton, SC 29325

Reference: Laboratory Test Report  
Lab Identification No. 35376  
Invoice No. 66580

Dear Mr. Jones:

One (1) fabric sample, identified as **EMMERLING WHITE FOR RADISSON (NINA NICKERSON)**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2019 Edition", (Cover Fabric Test). The results are as follows:

**Test Results**

Vertical Char Lengths

8mm

8mm

8mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

