

**Textile Testing**553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119Report Number: 59091
Date: 6-13-2013

For the Account Of: Richloom Fabrics
261 Fifth Avenue
New York, NY 10016

Contact: Melissa Ward

Client's Identification: LIAM

Test Performed **NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2009: Fabric Cover Test and UFAC Fabric Classification Test Method – 1990**

TEST DATA

Specimen #	Char Length (inches)
1	0.6
2	0.5
3	0.5

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 44 mm (1.75 in.) or less, the fabric is classified a UFAC and NFPA Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.), the fabric is classified a UFAC Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a UFAC Class II cover fabric.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested is:

- ☒ Class I
☐ Class II

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

**Textile Testing**553 76th Street - Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

TESTING CERT. #3193.01

Report Number: 59091

Date: 6-13-2013

For the Account Of: Richloom Fabrics
261 Fifth Avenue
New York, NY 10016
Contact: Melissa Ward

Client's Identification: A913F with Nano-Tex® & Acrylic Backing

Test Performed California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery Fabrics, March 2000

TEST DATA

☒ Plain Surface ☐ Raised Surface

Specimen	Flame Spread	Flame Spread
	Warp Face (seconds)	Warp Back (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

Specimen	Flame Spread	Flame Spread
	Fill Face (seconds)	Fill Back (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

ABBREVIATIONS USED

DNI Did not ignite when exposed to test ignition source
IBE Ignited but extinguished before burning through stop cord
SF Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric
TSF Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

ACCEPTANCE CRITERIA

1. **With nap** - Minimum flame spread of any individual specimens shall be 7 seconds. (ACT Criteria decreases minimum time to 4 seconds)
2. **Without nap** - Minimum flame spread of any individual specimens shall be 3.5 seconds.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature