

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 9, 2026

Mr. Kevin Jones
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 67063
Invoice No. 98332

Dear Mr. Jones:

One (1) fabric sample, identified as **Midas Mist**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2024 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

16mm

15mm

18mm

*Date Tested: February 9, 2026

*Conditioned minimum of 4 hours @ 70±5°F and <65% RH


The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

Lab Identification No. 67063

Sample Identification: **Midas Mist**



certificate of testing

client Richloom Bailey Plant
100 Bailey Plant Rd
Clinton, SC 29325
product identification Midas ALMO

test method performed smolder resistance of materials used in upholstered furniture – section 1: cover fabrics
california technical bulletin 117: 2013 (january 2019 revision)
date of test 9.20.2023

test results

specimen	char length (in.)	extinguished <45 min (y/n)
1	0.5	y
2	0.6	y
3	0.6	y

notes

test conditions 70 ±3.5%, 50 ±5% relative humidity requirement: 21 ±3°C, less than 55% relative humidity
sampling as received
ignition source srm1196a
deviations none

acceptance criteria

- pass
 - vertical char length ≤1.8 inches (45mm)
 - smoldering extinguishes within 45 minutes
 - no transition to open flaming
- fail
 - vertical char >1.8 inches (45mm)
 - smoldering beyond 45 minutes
 - specimens transition to open flaming
- retest
 - if only one of the three initial specimens fail, retest an additional three specimens
 - if all three additional specimens pass the test, the cover fabric passes the test
 - if any one of the additional three specimens fail, the cover fabric fails the test

classification

based upon the test results and acceptance criteria listed above, the product identified is a

- ☒ pass
- ☐ fail
- ☐ requires retesting

certification statement by signing below, the lab certifies that the results were obtained after testing specimens submitted by the client in accordance to the procedures and equipment specified by the standard stated above.

approved by: 