

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 31, 2022

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 50379
Invoice No. 81681

Dear Mr. Jones:

One (1) fabric sample, identified as **Shia Putty**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” ***Per your request, testing was modified by using flame retardant polyurethane foam.***

The sample submitted was tested to Section 3.1 Smouldering Cigarette Test. The results are as follows:

Test Results

(Smouldering Cigarette)

<u>#1</u>	<u>#2</u>
PASS	PASS
(No flaming ignition or progressive smouldering ignition)	(No flaming ignition or progressive smouldering ignition)


The sample submitted **meets** minimum requirements of the above standard when tested to the smouldering cigarette ignition source.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 31, 2022

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 50379
Invoice No. 81681

Dear Mr. Jones:

One (1) fabric sample, identified as **Shia Putty**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” ***Per your request, testing was modified by using flame retardant polyurethane foam.***

The sample submitted was tested to Section 3.2 Propane Flame Test. The results are as follows:

Test Results

(Propane Flame)

<u>#1</u>	<u>#2</u>
PASS	PASS
(No flaming ignition or progressive smouldering ignition)	(No flaming ignition or progressive smouldering ignition)


The sample submitted **meets** minimum requirements of the above standard when tested to the propane ignition source.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 9, 2019

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 37342
Invoice No. 68555

Dear Mr. Jones:

One (1) fabric sample, identified as **SHIA LEMON FOR FERGIE**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths

28mm

26mm

30mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 9, 2019

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 37342
Invoice No. 68555

Dear Mr. Jones:

One (1) fabric sample, identified as **SHIA LEMON FOR FERGIE**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2019 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

25mm

29mm

27mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

