

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 10, 2020

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 40611
Invoice No. 71864

Dear Mr. Jones:

One (1) fabric sample, identified as **SOOKIEFTG FOR HD VEGAS (ROSE AQUILA)**, was received and tested in accordance with the test procedures outlined. The results are as follows:

Test Procedures

Test Results

	<u>Warp</u>	<u>Fill</u>
Breaking Strength (lbf)		
ASTM D 5034-09 (Grab)	298.7	254.0
Tearing Strength (lbf)		
ASTM D 2261-13 (Tongue)	30.8	36.4
Yarn Slippage (lbf)		
ASTM D 4034-92	88.0	79.1
Resistance to Pilling		
ASTM 3511-16 (Brush)	4 – Slight Pilling	
Colorfastness to Crocking		
AATCC 8-2016	Dry – 5	
	Wet – 5	
Colorfastness to Light (40 hrs)		
AATCC 16.3-2014	Grade 4-5	
Surface Abrasion		
ASTM D 4966-12	Passed 60,000 Cycles*	
(Martindale)	*Testing was stopped at this point, sample had not failed.	
Surface Abrasion		
ASTM D 4157-13 (#10 Cotton Duck Abradant)	Passed 100,000 Cycles*	
4lb. Tension, 3lb. Load	*Testing was stopped at this point, sample had not failed.	


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 10, 2020

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 40611
Invoice No. 71864

Dear Mr. Jones:

One (1) fabric sample, identified as **SOOKIEFTG FOR HD VEGAS (ROSE AQUILA)**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths

15mm

15mm

17mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 10, 2020

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 40611
Invoice No. 71864

Dear Mr. Jones:

One (1) fabric sample, identified as **SOOKIEFTG FOR HD VEGAS (ROSE AQUILA)**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2019 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

14mm

14mm

15mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

