

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 5, 2018

Ms. Amy Bermudez
RICHLOOM FABRICS GROUP
261 Fifth Avenue
New York, NY 10016

Reference: Laboratory Test Report
Lab Identification No. 29050
Invoice No. 60218

Dear Ms. Bermudez:

One (1) fabric sample, identified as **PATTERN: CRAFTY PRINTED FRT-BK; COLOR: SPA**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths

10mm

13mm

11mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 5, 2018

Ms. Amy Bermudez
RICHLOOM FABRICS GROUP
261 Fifth Avenue
New York, NY 10016

Reference: Laboratory Test Report
Lab Identification No. 29050
Invoice No. 60218

Dear Ms. Bermudez:

One (1) fabric sample, identified as **PATTERN: CRAFTY PRINTED FRT-BK; COLOR: SPA**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2013 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

9mm 11mm 10mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

