

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

October 5, 2021

Mr. Logan Jones
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 47458
Invoice No. 78721

Dear Mr. Jones:

One (1) fabric sample, identified as **Rimo Grey Lot: 551573**, was received and tested in accordance with **IMO FTPC-2010; International Code for Application of Fire Test Procedures Resolution MSC.307 (88) Annex 1- Fire Test Procedures, Part 7- Test for Vertically Supported Textiles and Films**, “The test results relate to the behavior of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.”

The sample submitted was tested in accordance with Section 6; Test Procedure; sub-sections 6.1-6.4. The results are as follows:


Flame Determination - Warp

Surface Face	Sustained Flaming (Y/N)	Char Length (mm)	Surface Back	Sustained Flaming (Y/N)	Char Length (mm)	Edge	Sustained Flaming (Y/N)	Char Length (mm)
5 sec.	N	46	5 sec.	N	50	5 sec.	N	35
15 sec.	Y	103*	15 sec.	N	86	15 sec.	N	54

Flame Determination - Fill

Surface Face	Sustained Flaming (Y/N)	Char Length (mm)	Surface Back	Sustained Flaming (Y/N)	Char Length (mm)	Edge	Sustained Flaming (Y/N)	Char Length (mm)
5 sec.	N	60	5 sec.	N	46	5 sec.	N	55
15 sec.	N	100*	15 sec.	N	91	15 sec.	N	58

*DENOTES WORST TESTING CONDITION



336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

Test Results

	Specimen	Flame Reached Edge (Y/N)	Ignition of Cotton/Wool (Y/N)	Surface Flash (mm)	Afterflame (sec)	Char Length (mm)
<u>Warp</u>	1	N	N	0	0	83
	2	N	N	0	0	86
15 Sec. Face	3	N	N	0	5	94
	4	N	N	0	0	96
	5	N	N	0	0	93
	Average				1.0	90

	Specimen	Flame Reached Edge (Y/N)	Ignition of Cotton/Wool (Y/N)	Surface Flash (mm)	Afterflame (sec)	Char Length (mm)
<u>Fill</u>	1	N	N	0	0	104
	2	N	N	0	0	97
15 Sec. Face	3	N	N	0	0	85
	4	N	N	0	0	90
	5	N	N	0	0	96
	Average				0	94

The sample submitted **meets** the minimum requirements of the above standard. The afterflame time cannot exceed 5 seconds for any specimen. There can be no flame propagation to the edges for any specimen and no ignition of the cotton wool. Average char length cannot exceed 150mm and there can be no occurrence of a surface flash more than 100mm from the point of ignition.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 20, 2018

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 33250
Invoice No. 64410

Dear Mr. Jones:

One (1) fabric sample, identified as **KOPARFPF WHITE FOR MELISSA WARD**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u> <u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	0.11
2	0.0	0.17
3	0.0	0.11
4	0.0	0.29
5	0.0	1.08
6	0.0	0.40
7	0.0	0.34
8	0.0	0.23
9	0.0	0.29
<u>10</u>	<u>0.0</u>	<u>0.29</u>
AVG	0.0	0.33

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

