

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 14, 2022

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 49033
Invoice No. 80334

Dear Mr. Jones:

One (1) fabric sample, identified as **GRACE LINEN**, was received and tested in accordance with AATCC Test Method 16.3-2020, “Colorfastness to Light: Xenon-Arc”. The sample was tested for a total of 60 Standard Hours. The results are as follows:

Test Results After

60 Std. Hrs.


5

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 14, 2022

Mr. Logan Jones
RICHLOOM FABRICS GROUP
P.O. Box 1157
Clinton, SC 29325

Reference: Laboratory Test Report
Lab Identification No. 49033
Invoice No. 80334

Dear Mr. Jones:

One (1) fabric sample, identified as **GRACE LINEN**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	17.75
2	0.0	7.39
3	0.0	13.48
4	0.0	4.78
5	0.0	13.15
6	0.0	22.36
7	0.0	9.27
8	0.0	11.64
9	0.0	7.58
<u>10</u>	<u>0.0</u>	<u>5.03</u>
AVG	0.0	11.24

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

