

**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

October 31, 2019

Mr. Logan Jones  
RICHLOOM FABRICS GROUP  
P.O. Box 1157  
Clinton, SC 29325

Reference: Laboratory Test Report  
Lab Identification No. 38661  
Invoice No. 69866

Dear Mr. Jones:

One (1) fabric sample, identified as **VIVOLI GRAPHITE FOR ETHAN ALLEN**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

**Test Results**

Vertical Char Lengths

13mm

15mm

15mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

October 31, 2019

Mr. Logan Jones  
RICHLOOM FABRICS GROUP  
P.O. Box 1157  
Clinton, SC 29325

Reference: Laboratory Test Report  
Lab Identification No. 38661  
Invoice No. 69866

Dear Mr. Jones:

One (1) fabric sample, identified as **VIVOLI GRAPHITE FOR ETHAN ALLEN**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

**Test Results**

Vertical Char Lengths

16mm

12mm

13mm

The sample submitted **meets** the requirements of the above standard and is a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 44 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

