

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk



9630

TEST CERTIFICATE

CLIENT:	Interfabrics S.L Pol Ind Francisco Vitoria Calle Del Textil S/N 03830 Muro De Alcoy Alicante, Espana -	Certificate Number:	UPH250150 -2
		Date Received:	17/02/2025
		Date Issued:	21/02/2025
		Issue Number:	1
		Changes made from previous issue (if applicable)	
Contact:	Toni Fernandez		
Tel:	+34 637494453		
Email:	ajfernandez@aquaclean.com		

SAMPLE IDENTIFICATION

The information in this section is provided by the client and Lancashire Testing Services Ltd assumes no responsibility or liability for its accuracy.

Sample Name / Reference	Ward AC INFR SF
Additional Names:	-
Batch Ref/Number:	
Order Number:	APQP Sample
Colour:	-
Fabric Composition:	White-Brown
Quality:	89% Polyester, 8% Modacrylic, 3% Cotton

Additional Information: (Annex)

Name and address of sponsor:	-
Names and address of supplier/manufacturer:	-
Type of Furniture:	-
Fabric Details: (Weave/Density/Yarn count/thickness (mm)/mass (g/m ²) colour & tone	-
Fire Retardant Treatment:	-

SPECIFICATION

IMO FTP CODE 2010 Annex 1 Part 8 - Test for upholstered furniture

TEST METHOD

Flammability:	IMO FTP CODE 2010 - Annex 1 - Part 8 - Test for upholstered furniture
Pre-treatment:	None Required

Conclusion

The sample tested: **Complies** with the flammability requirements of:
IMO FTP Code 2010 - Annex 1 - Part 8 - Test for upholstered furniture, taking into account uncertainty of measurement, when tested as suggested in appendix 3 of the IMO FTP Code 2010 over a non-flame-retardant filling (RP21130)

Uncertainty of Measurement: ±1 second - timing measurements, ±1mm - dimensional measurements

Comments:

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk

9630

TEST CERTIFICATE**Test Results:-****IMO FTP Code 2010 - Part 8 - Test for upholstered furniture**

"The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use."

Sample Code			UPH250150 -2						
Sample Name / Reference			Ward AC INFR SF						
Client			Interfabrics S.L						
Date of test			21/02/2025						
Pre-Treatment			None Required -						
Filling Type			Carpenter/RP21130 unmodified polyurethane foam of density 20-22Kg/m³/Type B, 130						
Size of test rig			Small: Back - 450 x 300 ± 2mm + Seat - 450 x 150 ± 2mm						
Test Conditions			Period h	Temperature °C		Relative humidity %		Air Flow m/s	Volume m³
Conditioning of test specimens			≥16	23±2		50±5		≤0.2	-
Testing conditions			-	20±5		20-70		0.04	≥6
Testing Source			Smouldering Cigarette Source						
Cigarette Specification			Length = 70±4mm, Diameter = 8±0.5mm, mass = 0.95 ±0.15g, Smouldering rate = 11±4.0 min/50mm						
Testing time limit			60 minutes after placement of smouldering cigarette.						
Test No.	Position	Ignition/N on Ignition	Duration of: (min.sec)			Extent of Damage:			
			Ignition Source	Flames	Smoke	Base: Length (mm)	Base: Width (mm)	Back: Length (mm)	Back Width (mm)
1	LHS	NI	16.33	-	17.06	-	-	-	-
2	RHS	NI	16.54	-	17.38	-	-	-	-
Testing Source			Propane Flame Ignition Source / Butane ignition source						
Testing time limit			2 minutes after removal of burner tube (120 seconds)						
Test No.	Position	Ignition/N on Ignition	Duration of: (min.sec)			Extent of Damage:			
			Ignition Source	Flames	Smoke	Base: Length (mm)	Base: Width (mm)	Back: Length (mm)	Back Width (mm)
1	RHS	NI	20	1	19	14	21	68	20
2	LHS	NI	20	1	21	15	20	70	21
RESULT: SMOULDERING CIGARETTE SOURCE								PASS	
PROPANE/BUTANE FLAME IGNITION SOURCE								PASS	
KEY: I = Ignition, NI = Non Ignition, LHS = Left hand side, M = Middle, RHS = Right hand side									

Craig Allardice Laboratory Technician	John Marsh Laboratory Supervisor	Peter Collings Operations Manager

Please note that copies of this original certificate are not valid

Issue Number: 1

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk

9630

TEST CERTIFICATE**Certificate Number:** UPH250150-2**Date of Issue:** 21/02/2025**Decision Rule:**

Lancashire Testing Services have measurement uncertainties for all test standards (available on request) and have applied these measurements to the test result.

The specific level of risk is < 2.5% as stated in ILAC-G8:09/2019. Unless otherwise indicated L.T.S will apply this rule to all measurements reported.


A binary decision rule which is guard banded by the test measurement uncertainty is used. If the measurement result plus/minus the expanded uncertainty with a 95 % coverage probability overlaps the limit, it is not possible to state compliance or non-compliance. The measurement result and the expanded uncertainty with a 95 % coverage probability will then be reported. The report will include the actual value with the uncertainty range.

Lancashire Testing Services Ltd have conducted thorough analysis of the uncertainty of all measurements carried out in the application of the standard or standards detailed in this report. Where possible any associated uncertainty of measurements have been accounted for in the working instructions, so that they have no impact on the reporting of the final result. In instances where uncertainty of measurements can only be taken into account after the test has been conducted, these uncertainty values have been stated on this report. The stated uncertainty of measurement has also been taken into account in the final reporting of the overall result.

Information provided about a customer, from a source other than the customer, shall only be shared with the customer. The provider of the information shall remain confidential to the laboratory unless agreed by the source of the information.

Issue Number: 1

Please note that copies of this original certificate are not valid



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 19, 2025

Mr. Miquel Cardona
AQUACLEAN USA INC.
834 Huffman Street
Greensboro, NC 27405

Reference: Laboratory Test Report
Lab Identification No. 63317
Invoice No. 94630

Dear Mr. Cardona:

One (1) fabric sample, identified as **WARD**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
15mm	15mm	15mm


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 19, 2025

Mr. Miquel Cardona
AQUACLEAN USA INC.
834 Huffman Street
Greensboro, NC 27405

Reference: Laboratory Test Report
Lab Identification No. 63317
Invoice No. 94630

Dear Mr. Cardona:

One (1) fabric sample, identified as **WARD**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2024 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

12mm

14mm

14mm

*Date Tested: February 18, 2025

*Conditioned minimum of 4 hours @ 70±5°F and >65% RH

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

