

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 4, 2026

Mr. Kevin Jones
RICHLOOM FABRICS GROUP
100 Bailey Plant Road
Clinton, NC 29325

Reference: Laboratory Test Report
Lab Identification No. 68417
Invoice No. 99666

Dear Mr. Jones:

One (1) fabric sample, identified as **SACO PFP Lot: 54604**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	27.93
2	0.0	28.21
3	0.0	32.58
4	0.0	10.61
5	0.0	25.28
6	0.0	29.91
7	0.0	17.30
8	0.0	34.00
9	0.0	9.15
<u>10</u>	<u>0.0</u>	<u>43.71</u>
AVG	0.0	25.87


The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

Lab Identification No. 68417

Page 2

Sample Identification: **SACO PFP Lot: 54604**

